

WAKULLA MAT  
155 WELDON PKWY STE 117 MARYLAND HEIGHTS MO 63043

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A)Spaghetti mat

Sample Color : (A)grey

Sample Receiving Date : Dec 21, 2021 &Dec 24, 2021

Testing Period : Dec 24, 2021 - Jan 05, 2022

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the sample(s) tested, for further details, please refer to the following page(s).

Test Performed : Selected test(s) as requested by applicant



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: [CN.Docccheck@sgs.com](mailto:CN.Docccheck@sgs.com)

1/F, Building 2, No.9, Yongfeng Road, Qinhuai District, Nanjing, China 210014 t (86-25) 84556406 f (86-25) 84553467 [www.sgsgroup.com.cn](http://www.sgsgroup.com.cn)

中国·南京·秦淮区永丰大道9号2幢1层 邮编: 210014 t (86-25) 84556406 f (86-25) 84553467 e [sgs.china@sgs.com](mailto:sgs.china@sgs.com)

Conclusion	A	Remark
Flammability Test	PASS	
Slip Resistance	See Results	

Remark(s) : PASS=Meet General Requirement

Signed for and on behalf of  
SGS-CSTC Standards Technical Services Co., Ltd. Nanjing Branch



Bella Zhou (Account Executive)



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: [CN.Docccheck@sgs.com](mailto:CN.Docccheck@sgs.com)

## Test Result

**Slip Resistance#**

(ASTM F609-05(Reapproved 2013); )

DryClay Tile

	Unit	A	Requirement
Coefficient of Friction	-	-	-
Static	-	0.58	-

WetClay Tile

	Unit	A	Requirement
Coefficient of Friction	-	-	-
Static	-	0.50	-

## Remarks:

1. The performance of slip resistance can be affected by surface roughness, presence of water, contaminants such as grease and other foreign materials, and floor surface wear over time.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: [CN.Docccheck@sgs.com](mailto:CN.Docccheck@sgs.com)

SGS-CSTC Inspection & Testing Services Co., Ltd.  
Nanjing Branch Textile Laboratory

1/F, Building 2, No.9, Yongfeng Road, Qinhuai District, Nanjing, China 210014      t (86-25) 84556406      f (86-25) 84553467      [www.sgsgroup.com.cn](http://www.sgsgroup.com.cn)  
中国·南京·秦淮区永丰大道9号2幢1层      邮编: 210014      t (86-25) 84556406      f (86-25) 84553467      e [sgs.china@sgs.com](mailto:sgs.china@sgs.com)

**The Surface Flammability Of Carpets And Rugs (FF1-70) #**

(Ref.16 CFR PART 1630-2007)

A

As received

Specimen	Shortest distance between the edge of the hole and the damaged area (mm)
1	93
2	95
3	90
4	92
5	91
6	93
7	90
8	92
Number of specimens in which the shortest distance $\leq$ 25.4mm	NIL

**Flammability requirement:**

1. A specimen passes the test if the charred portion does not extend to within 2.54cm (1.0 in.) of the edge of the hole in the flattening frame at any point.
2. At least seven of the eight specimens shall meet the test criterion in order to conform with this Standard.

**#: This test was carried out by SGS-CSTC Shanghai lab.**

The statement of conformity in this test report is only based on measured values by the laboratory and does not take their uncertainties into consideration.

\*\*\*End of Report\*\*\*



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 8307 1443, or email: CN.Docccheck@sgs.com**

SGS-CSTC Shanghai Technical Services Co., Ltd.  
Nanjing Branch Textile Laboratory

1/F, Building 2, No.9, Yongfeng Road, Qinhuai District, Nanjing, China 210014      t (86-25) 84556406      f (86-25) 84553467      [www.sgsgroup.com.cn](http://www.sgsgroup.com.cn)  
中国·南京·秦淮区永丰大道9号2幢1层      邮编: 210014      t (86-25) 84556406      f (86-25) 84553467      e [sgs.china@sgs.com](mailto:sgs.china@sgs.com)